42/348

5

- 1. Foamed polycrystalline silicon which has bubbles therein and an apparent density of  $2.20~\mathrm{g/cm^3}$  or less.
- 2. The foamed polycrystalline silicon of claim 1 which is in the form of an assembly of independent grains or an agglomerate of independent grains.
- 10 3. The foamed polycrystalline silicon of claim 2, wherein the assembly of independent grains contains independent grains each having a weight of 0.2 to 2 g in an amount of 50 g or more based on 100 g.
- 15 4. The foamed polycrystalline silicon of claim 2, wherein the assembly of independent grains is formed by breaking up the agglomeration of an agglomerate of independent grains.
- The foamed polycrystalline silicon of claim 1, wherein
  a plurality of independent bubbles are contained and are existent in a center portion of a grain.
  - 6. A crushed product of the foamed polycrystalline silicon of claim 1.
  - 7. The crushed product of claim 6 which has an average grain diameter of more than 200 µm and 5 mm or less.
- 8. A method of producing foamed polycrystalline silicon comprising naturally dropping droplets of silicon containing hydrogen which has been molten in the presence of hydrogen in 0.2 to 3 seconds and cooling the droplets until hydrogen bubbles are locked up in the droplets.

LOCKSY, OLLICE

...

18/1/

15

20

- 9. The method of claim 8, wherein natural dropping is carried out for 0.2 to 2 seconds.
- 10. The method of claim 8, wherein a silicon deposition 5 reaction between hydrogen and a chlorosilane and a reaction for melting the deposited silicon in the presence of hydrogen are carried out simultaneously to prepare silicon droplets containing the hydrogen.
- 10 11. A polycrystalline silicon production apparatus comprising:
  - (a) a cylindrical vessel having an opening which is a silicon take-out port at the lower end;
  - (b) a heater for heating the inner wall from the lower end to a desired height of the cylindrical vessel at a temperature equal to or higher than the melting point of silicon:
  - (c) a chlorosilane feed pipe which is composed of an inner pipe having a smaller outer diameter than the inner diameter of the cylindrical vessel and constituted such that one opening of the inner pipe faces down in a space surrounded by the inner wall heated at a temperature equal to or higher than the melting point of silicon; and
- (d) a first seal gas feed pipe for supplying seal gas into a space defined by the inner wall of the cylindrical vessel and the outer wall of the chlorosilane feed pipe.
- 12. The apparatus of claim 11 which further comprises (e) a hydrogen gas feed pipe for supplying hydrogen gas into the30 above cylindrical vessel.
- 13. The apparatus of claim 11, wherein a cooling acceptor for receiving droplets falling from the lower end of the cylindrical vessel is disposed in a lower portion of the

5

10

cylindrical vessel with a space therebetween.

14. The polycrystalline silicon production apparatus of any one of claims 11 to 13 further comprising a closed vessel which covers at least a lower end portion of the cylindrical vessel, forms a space in the lower portion of the cylindrical vessel and is provided with an exhaust gas discharge pipe, and a second seal gas feed pipe for supplying seal gas into a space defined by the outer wall of the cylindrical vessel and the inner wall of the closed vessel.